

In the claims:

Please amend the following claims:

---

D<sub>1</sub>

1.(twice amended) A process for forming a hollow article, comprising:

providing a mixture of metal and ceramic powders, lubricants, and binders, that form a feedstock;

forming a first molded part that has an outer surface;

through powder injection molding of the feedstock, forming a second molded part that is in contact with said outer surface;

disposing of the first molded part through ash-free combustion; and

heating the second molded part whereby sintering occurs and said hollow article is formed.

---

D<sub>2</sub>

6.(twice amended) A process for forming a hollow article, comprising;

providing a mixture of metal and ceramic powders, lubricants, and binders, that form a feedstock;

providing tooling that is able to injection mold from a first barrel into a first mold and from a second barrel into a second mold;

using a material, injected from the first barrel into the first mold, forming a first molded part that has an outer surface;

AMT00-001C

D2  
through powder injection molding of the feedstock from the second barrel into the second mold, forming a second molded part that is in contact with said outer surface;  
disposing of the first molded part through ash-free combustion; and  
heating the second molded part whereby sintering occurs and said hollow article is formed.

---

D3  
11.(twice amended) A process for forming a hollow article, comprising;

providing a mixture of metal and ceramic powders, lubricants, and binders, that form a feedstock;

providing first and second tooling, one being able to injection mold from a first barrel into a first mold and one being able to injection mold from a second barrel into a second mold;

in the first tooling, using a material, injected from the first barrel into the first mold, forming a first molded part that has an outer surface;

transferring the first molded part to the second tooling;

in the second tooling, through powder injection molding of the feedstock from the second barrel into the second mold, forming a second molded part that is in contact with said outer surface;

disposing of the first molded part through ash-free combustion; and

heating the second molded part whereby sintering occurs and said hollow article is formed.